

Grade E
KEY LARGO

QUARRY
KL026

JONQUIL
KL022

CAYENNE
KL019

AEGEAN
KL014

PALM
KL013

SANDSTONE
KL020

GRAPHITE
KL006

TANGERINE
KL009

RASPBERRY
KL011

ULTRAMARINE
KL004

NASSAU
KL024

PEAR
KL033

EBONY
KL016

INFORMATION TECHNIQUE

Patron - Largeur	Composition	Finis	Abrasion (D.F.)	Résistance à la lumière	Code de nettoyage
KEY LARGO - 54" 	86% Vinyle sans Phthalate 14% Polyester à l'endos	Antitache Surface résistante à l'encre	250,000 [^]	650 Heures Classe 4.5	WS, BC, CFC

CODE DE NETTOYAGE

- **WS:** Utiliser un agent nettoyant à base d'eau ou de mousse.
- **BC:** Préparer une solution contenant 10% d'agent de blanchiment, nettoyer pour un maximum de 10 minutes et rincer rapidement avec de l'eau.
- **CFC:** Veuillez consulter le site web de Mayer pour de plus amples informations.

INFORMATION ADDITIONNELLE

[^]**Abrasion:** Plusieurs facteurs affectent la durabilité et l'apparence des recouvrements, notamment l'usage et l'entretien du produit. Les résultats de test Wyzenbeek supérieurs à 100.000 double frottements n'ont pas démontré être une mesure fiable de la longévité d'un recouvrement. Veuillez consulter le site web de Mayer pour d'autres spécifications techniques.

TECHNICAL INFORMATION

Width - Pattern	Content	Finish	Abrasion (D.F.)	Lightfastness	Cleaning Code
KEY LARGO - 54" 	86% Vinyl Phthalate Free face, 14% Polyester backing	Soil & Stain Resistant Top Coat with Ink Resistant Technology	250,000 [^]	650 Heures Classe 4.5	WS, BC, CFC

CLEANING CODE

- **WS:** Use water-based or foam cleaning agent, or pure water-free solvent.
- **BC: Bleach Cleanable** – 1 part bleach, 9 parts water = 10% bleach, 90% water solution. Do not clean/disinfect fabric for longer than minutes using the 10% bleach solution. Always rinse promptly with clean water after applying the bleach solution. Failure to do so will void any and all warranties.
- **CFC:** Coated Fabrics Cleaning – Refer to Mayer website for complete cleaning info.


ADDITIONAL INFORMATION

Abrasion: Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance. Wyzenbeek results above 100,000 double rubs have not been shown to be a reliable indicator of increased fabric lifespan. Specifications: Specifications are correct at the time of printing. Additional specifications are available on our website.



10871, avenue Salk
Montréal-Nord
(Québec) Canada
H1G 6M7

bouty.com



MAYERFABRICS

TF 800.428.4415



3450, 1re Rue
Saint-Hubert
(Québec) Canada
J3Y 8Y5

adi-artdesign.com